



Teflon™ FEP

Fluoropolymer Film

Properties Bulletin

Description

Teflon™ FEP film is a transparent, thermoplastic film that can be heat sealed, thermoformed, vacuum formed, heat bonded, welded, metalized, and laminated to many other materials, as well as used as an excellent hot-melt adhesive.

This wide variety of fabrication possibilities combines with the following important properties to offer a unique balance of capabilities not available in any other plastic film.

Chemical Compatibility

- Teflon™ FEP film is chemically inert and resistant to virtually all chemicals, except molten alkali metals, gaseous fluorine, and certain complex halogenated compounds, such as chlorine trifluoride, at elevated temperatures and pressures.
- Low permeability to liquids, gases, moisture, and organic vapors

Electrical Reliability

- Superior reliability and retention of properties over large areas of film
- High dielectric strength, over 6,500 V/mil for 1-mil film (260 kV/mm for 0.025-mm film)
- No electrical tracking, non-wetting, and/or non-charring
- Very low power factor and dielectric constant, only slight change over wide ranges of temperature and frequency

Wide Thermal Range

- Continuous service temperature: -240 to 205 °C (-400 to 400 °F)
- Melting range: 250 to 280 °C (500 to 540 °F)
- Heat sealable

Mechanical Toughness

- Superior anti-stick and low frictional properties
- High resistance to impact and tearing
- Useful physical properties at cryogenic temperatures

Long Time Weatherability*

- Inert to outdoor exposure; no measurable change after 20 years in Florida
- High transmittance of ultraviolet and all, but far, infrared radiation

Reliability

- Teflon™ FEP film contains no plasticizers or other foreign materials.
- Conventional equipment and techniques can be used for processing; basic composition and properties will not be influenced.
- Rigid quality control by Chemours ensures uniform gauge, void-free film.

Shelf Life

The shelf life of Teflon™ FEP fluoropolymer film is:

- Unlimited in terms of the mechanical, chemical, thermal and electrical properties
- 12 months from the date of treatment for the effectiveness of the surface treatment (types C and C20)

Table 1. Types and Gauges of Teflon™ FEP Fluoropolymer Film

	Gauge								
	50	100	175	200	300	500	750	1000	2000
Thickness, mil	0.5	1	1.75	2	3	5	7.5	10	20
Thickness, μm	12.5	25	44	50	75	125	190	250	500
Approx. area factor, ft ² /lb	180	90	51	45	30	18	12	9	4.5
Approx. area factor, m ² /kg	36	18	10.3	9	6.4	3.8	2.5	1.9	0.95
Availability									
Type A—FEP, general-purpose	X	X	X	X	X	X	X	X	X
Type C—FEP, one side cementable	—	X	X	X	X	X	—	—	—
Type C-20—FEP, both sides cementable	—	X	—	X	—	X	—	—	—

Note: Each roll of Teflon™ film is clearly identified as to resin type, film thickness, and film type.
 FEP: Resin type 500: Film thickness, 500 gauge, 5 mil C: Film type, cementable one side

Typical Properties of Teflon™ FEP Fluoropolymer Film

Property	Test Method	Typical Value ^a	
		SI Units	English Units
Mechanical			
Tensile Strength at Break	D882	21 N/mm ²	3000 psi
Elongation at Break	D882		300%
Yield Point	D882	12 MPa	1700 psi
Elastic Modulus	D882	480 MPa	70,000 psi
Impact Strength	Chemours pneumatic impact tester	7.7 X 10 ³ J/m	144 ft-lb/in
Folding Endurance (MIT)	D2176		10,000 cycles
Tear Strength—Initial (Graves)	D1004	2.65 N	270 g force
Tear Strength—Propagating (Elmendorf)	D1922	1.23 N	125 g
Bursting Strength (Mullen)	D774	76 kPa	11 psi
Thermal			
Melt Point	D3418 (DTA)	260–280 °C	500–536 °F
Zero Strength Temperature ^b		255 °C	490 °F
Coefficient of Thermal Conductivity	Cenco-Fitch	0.195 W/(m·K)	1.35 Btu-in/(hr·ft ² ·°F)
Specific Heat	—	1172 J/(kg·K)	0.28 Btu/(lb·°F)
Heat Deflection Temperature at 0.46 N/mm ² (66 psi)	D648 Tensile Bars	70 °C	158 °F
at 1.82 N/mm ² (264 psi)		51 °C	124 °F
Dimensional Stability	30 min at 150 °C (302 °F)	MD = 0.72% expansion TD = 2.2% shrinkage	
Flammability Classification ^c	ANSI/UL 94	VTM-0	
Oxygen Index	D2863	95%	

^aFor 0.025 mm (1 mil) film at 25 °C (77 °F), unless otherwise specified.

^bTemperature at which a film supports a load of 0.14 N/mm² (20 psi) for 5 sec.

^cThis classification rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

Typical Properties of Teflon™ FEP Fluoropolymer Film (cont'd.)

Property	Test Method	Typical Value ^a	
		SI Units	English Units
Electrical			
Dielectric Strength, short-time, in air at 23 °C (73 °F), 6.35 mm (1/4 in) diameter electrode, 0.79 mm (1/32 in) radius 60 Hz, 500 V/s rate of rise: 0.025 mm (1 mil) film 0.5 mm (20 mil) film	ASTM D149 Method A	260 kV/mm 70 kV/mm	6500 V/mil 1800 V/mil
Dielectric Constant 25 °C (77 °F), 100 Hz–1 MHz –40–225 °C (–40–437 °F), 1000 Hz	ASTM D150		2.0 1.93–2.02
Dissipation Factor 25 °C (77 °F), 100 Hz–1 MHz –40–225 °C (–40–437 °F), 1000 Hz –40–240 °C (–40–464 °F), 1 MHz	ASTM D150		0.0002–0.0007 0.0002 0.0005
Volume Resistivity –40–240 °C (–40–464 °F)	ASTM D257		>1 X 10 ¹⁸ ohm·cm
Surface Resistivity –40–240 °C (–40–464 °F)	ASTM D257		>1 X 10 ¹⁶ ohm/sq
Surface Arc Resistance	ASTM D495		>165 sec ^b
Insulation Resistance at 100 °C (212 °F) at 150 °C (302 °F) at 200 °C (392 °F)	Based upon 0.2 MF wound capacitor sections, using single layer, Teflon™ 50A film		350,000 Mohm·µF 250,000 Mohm·µF 65,000 Mohm·µF
Chemical			
Moisture Absorption	—		<0.01%
Weatherability	Continuous exposure in Florida		No adverse effects after 20 yr
Permeability, Gas: Carbon Dioxide Hydrogen Nitrogen Oxygen	ASTM D1434		cm ³ /m ² ·24 hr·atm ^c 25.9 X 10 ³ 34.1 X 10 ³ 5.0 X 10 ³ 11.6 X 10 ³
Permeability, Vapor: Acetic Acid Acetone Benzene Carbon Tetrachloride Ethyl Alcohol Hexane Water	ASTM E96	g/m ² ·d	g/100 in ² ·24 hr 6.3 14.7 9.9 4.8 10.7 8.7 7.0

^aFor 0.025 mm (1 mil) film at 25 °C (77 °F), unless otherwise specified.

^bSamples melted in arc did not track.

^cTo convert to cm³/(100 in²·24 hr·atm), multiply by 0.0645.

Teflon™ FEP fluoropolymer is chemically inert and solvent-resistant to virtually all chemicals, except molten alkali metals, gaseous fluorine, and certain complex halogenated compounds, such as chlorine trifluoride, at elevated temperatures and pressures.

Property Values of Teflon™ FEP Fluoropolymer Film (cont'd.)

Property	Test Method	Typical Value*	
		SI Units	English Units
Miscellaneous			
Density	ASTM D1505	2150 kg/m ³	134 lb/ft ³
Coefficient of Friction, Kinetic (Film-to-Steel)	ASTM D1894	0.1-0.3	
Refractive Index	ASTM D542	1.341-1.347	
Solar Transmission	ASTM E-424	96%	

*For 0.025 mm (1 mil) film at 25 °C (77 °F), unless otherwise specified.

HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Teflon™ is a registered trademark of Chemours for its brand of fluoropolymer resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit www.teflon.com/license

CAUTION: Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/industrial

For sales and technical support contacts, visit teflon.com/industrialglobalsupport

© 2025 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-26941-1

C-10597 (4/25)